



Contribution ID : 55

Type : not specified

## Towards understanding the magnetic structure of DyN, a ferromagnetic semiconductor

Towards understanding the magnetic structure of DyN, a ferromagnetic semiconductor

Jacob P. Evans, 1 Glen Stewart, 2 Sean Cadogan, 2 Wayne Hutchison, 2 Emma Mitchell 3 and James E. Downes, 1

1. MQ Photonics Research Centre, Department of Physics and Astronomy – Macquarie University, NSW 2109, Australia
2. School of Physical, Environmental and Mathematical Sciences, UNSW Canberra – at the Australian Defence Force Academy, Canberra BC, ACT 2600, Australia
3. Materials Science and Engineering, CSIRO, NSW 2070, Australia

The rare-earth nitride (REN) series has attracted considerable research interest because of the co-existence of semiconducting and ferromagnetic properties, a feature ideal for spintronic devices. Dysprosium nitride (DyN) is a promising candidate whose electronic structure is relatively well understood. However, its magnetic structure has received little attention until recently. In particular, its low temperature bulk magnetic moment of about 4  $\mu_B$ /ion is significantly lower than the predicted magnetic moment, which is much closer to the free-ion value of 10  $\mu_B$ /ion [1]. Because of this, we are attempting to understand the detailed magnetic structure of DyN using conventional magnetometry combined with  $^{161}\text{Dy}$  Mössbauer spectroscopy.

Using ion-assisted deposition, we have grown thick 3-4  $\mu\text{m}$  DyN films on both sapphire and Kapton substrates. Because the characteristic measurement time for  $^{161}\text{Dy}$  Mössbauer spectroscopy is of the order of nanoseconds, the spectrum recorded at 5 K was sensitive to rapid thermal fluctuation between the low-lying levels of the Dy $^{3+}$  crystal field scheme. The spectrum was successfully analysed in terms of flipping between a pair of levels with moments of the same magnitude, 10  $\mu_B$ , but opposite sign. Based on the fitted energy separation, the longer-time, thermal-averaged moment can be estimated at about 85% of the full free ion value. However, such a simple 2-level crystal field ground state model would require a breaking of the cubic symmetry appropriate for the Dy $^{3+}$  site in bulk DyN.

References:

[1] D. L. Cortie et. al., Phys. Rev. B 89, 064424 (2014)

The Mössbauer sources employed in this work were prepared at the OPAL reactor with the support of AINSE, grant number 14511.

**Primary author(s) :** Mr EVANS, Jacob (Macquarie University)

**Co-author(s) :** Dr MITCHELL, Emma (CSIRO); Dr STEWART, Glen (UNSW Canberra); Dr DOWNES, James (Macquarie University); Prof. CADOGAN, Sean (UNSW Canberra); Dr HUTCHISON, Wayne (UNSW Canberra)

**Presenter(s) :** Mr EVANS, Jacob (Macquarie University)