



USER MEETING 2016

24-25 NOVEMBER

National Centre for Synchrotron Science



Ansto

Australian Synchrotron

Contribution ID : 231

Type : Oral

The Evolution of Surface Silica Nanoparticles on Coated Steel Surfaces under High UV and High Humidity Environments Observed Using Synchrotron Macro ATR-FTIR Microspectroscopy

Thursday, 24 November 2016 14:15 (15)

Corrosion of metallic surfaces is prevalent and of great concern in a wide range of industries, particularly those in transport, aviation, building and food sectors, reportedly responsible for a direct cost of \$276 billion per annum(1). Galvanization has been widely used as a corrosion preventative method by coating the metallic surfaces with zinc that serves as a physical barrier to prevent corrosive substances from reaching the underlying metal. In tropical and sub-tropical climates with prolonged exposure to high UV and high humidity, thermosetting polymer coatings based on polyesters have also been used to provide an additional protection to the galvanized metal. This prevents the build-up of moisture within the pits present on the metallic surface where the zinc oxide passive film is weak, leading to localized corrosion(2). Recent advances in surface engineering using silica nanoparticles (SiO₂NPs) have allowed the development of innovative and highly functional surface coatings with enhanced corrosion resistance and durability(3). Nevertheless, long-term effect of environmental factors upon these materials remains unknown.

In this study, chemical evolution of SiO₂NPs-embedded polyester coatings on steel substrata was analysed after 5 years of exposure to tropical/sub-tropical environments in Singapore and Australia using synchrotron-based macro ATR-FTIR microspectroscopy and surface topographic techniques. Principal component analysis (PCA) based on FTIR spectral data observed at 9% SiO₂NPs shows differences in their response to environmental factors between the control group and the surfaces subjected to 3-year exposure. The clustering feature suggests changes in molecular structure of the coating resulted from the exposure, which principally involved triazine ring vibration in the melamine resins. Such molecular evidence corroborates well with the fact that the triazine ring is very sensitive to hydrolysis, particularly under high humidity conditions in tropical environments.

Indico rendering error

Could not include image: Problem downloading image (<https://owncloud.synchrotron.org.au/index.php/s/7h>)

References:

1. G. H. Koch *et al.*, Corrosion Costs and Preventive Strategies in USA, *Materials Performance*, Federal Highway Administration, VA, 2002.
2. R. Winston Revie *et al.*, *Corrosion and Corrosion Control*, John Wiley & Sons, 2008, 333-365.
3. M. J. Hollamby *et al.*, *Advanced materials*, 2011, 23, 1361-1365.

Keywords or phrases (comma separated)

Synchrotron infrared, surface coating, steel, polyester, nanoparticles

Are you a student?

No

Do you wish to take part in the Student Poster Slam?

No

Are you an ECR? (<5 yrs since PhD/Masters)

No

What is your gender?

Female

Primary author(s) : Dr VONGSVIVUT, Jitraporn (Pimm) (Infrared Microspectroscopy (IRM) Beamline, Australian Synchrotron, 800 Blackburn Road, Clayton, Victoria 3168, Australia)

Co-author(s) : Prof. IVANOVA, Elena (School of Science, Faculty of Science, Engineering and Technology, Swinburne University of Technology, Hawthorn, Victoria 3122, Australia); Dr TOBIN, Mark (Infrared Microspectroscopy (IRM) Beamline, Australian Synchrotron, 800 Blackburn Road, Clayton, Victoria 3168, Australia); Prof. J. CRAWFORD, Russell (School of Science, RMIT, Melbourne, Victoria, 3000, Australia); Dr MACLAUGHLIN, Shane (BlueScope Steel Research, Port Kembla, New South Wales 2505, Australia); Dr TRUONG, Vi Khanh (School of Science, Faculty of Science, Engineering and Technology, Swinburne University of Technology, Hawthorn, Victoria 3122, Australia)

Presenter(s) : Dr VONGSVIVUT, Jitraporn (Pimm) (Infrared Microspectroscopy (IRM) Beamline, Australian Synchrotron, 800 Blackburn Road, Clayton, Victoria 3168, Australia)

Session Classification : Concurrent Session 2: Surfaces

Track Classification : Surfaces