



Contribution ID : 33

Type : **Oral Presentation**

## **Activation energy for parabolic corrosion kinetics of Zircaloy-4 by consecutive hydrogen measurement at 30 – 80°C**

*Monday, 30 October 2017 17:45 (15)*

On the issue related on a safe disposal of spent fuel claddings is the corrosion and the subsequent gas and radionuclides release. The Zircaloy corrosion under a prospected disposal condition has recently been investigated by sensitive hydrogen measurements at 30°C, and reported that the kinetics in the rate around nm/y follows the parabolic rate law.

In the present work, an improved equipment to be usable even at higher temperatures up to 80°C has been applied for measuring hydrogen gas generated from Zircaloy-4 corrosion for 90 days. The Arrhenius relation of the parabolic rate constants for the corrosion kinetics has showed the activation energy of  $84.4 \pm 8.4$  kJ/mol, the value of which is lower than that for the general pre-transition corrosion under the in-pile temperature above 260°C (i.e. 113-135 kJ/mol), suggesting that simple mass transfer through a thin and firm oxide film is limiting the low temperature corrosion of Zircaloy.

### **Summary**

**Primary author(s) :** Dr SAKURAGI, Tomofumi (Radioactive Waste Management Funding and Research Center)

**Co-author(s) :** Mr KATO, Osamu (Kobe Steel, Ltd.); Mr YOSHIDA, Satoshi (Kobe Steel, Ltd.); Mr TATEISHI, Tsuyoshi (Kobelco Research Institute, Inc.)

**Presenter(s) :** Dr SAKURAGI, Tomofumi (Radioactive Waste Management Funding and Research Center)

**Session Classification :** Spent Fuel & Zircaloy Cladding

**Track Classification :** National and international collaborative waste management programs