



Contribution ID : 69

Type : **Oral Presentation**

Simplified UK Magnox waste glass alteration layer characterisation using ^{29}Si , ^{17}O and ^{25}Mg NMR techniques

Tuesday, 31 October 2017 14:00 (15)

The magnesium content of UK Magnox waste glass makes its aqueous durability much poorer than glasses such as SON68, which does not contain Mg. The glass dissolution kinetics is ultimately dependent on the composition/structures of the altered layers(1), here we try to elucidate formation mechanisms.

Alteration layers formed by in-situ precipitation have been discussed widely(2,3), but any direct identification of precipitated phases is not yet known. The altered layers of simplified Magnox waste glasses were examined using a variety of ^{17}O , ^{25}Mg and ^{29}Si solid-state NMR techniques. In terms of quantification and species identification, the Mg containing glass incorporates 3-4 times the amount of ^{17}O derived from the ^{17}O enriched leachate compared with a Ca glass, identified as bridging oxygen and hydroxyl oxygen species. At least two types of amorphous surface phases were characterised by proton cross-polarisation (CP) that show local environments similar to clay mineral phases(4). ^{25}Mg and ^{29}Si NMR spectra corroborate the active chemical role of Mg in precipitation and the multiphase nature of the alteration layer.

1. Curti, E. et al. (2006) Applied Geochemistry 21 pp. 1152-1168
2. Geisler, T (2010) Journal of Non-Crystalline Solids 356 pp. 1458-1465
3. Hellmann, R (2015) Nature Materials 14 pp. 307-311
4. Thien, B. et al. (2010) Applied Clay Science 49 pp. 135-141

Summary

Primary author(s) : Mr GUO, Rui (University of Cambridge)

Co-author(s) : Dr FARNAN, Ian (University of Cambridge)

Presenter(s) : Mr GUO, Rui (University of Cambridge)

Session Classification : Glass Wasteforms

Track Classification : National and international collaborative waste management programs